



Sovereign SX70 Woodstain

A high quality solvent based woodstain, containing a flexible alkyd resin along with water repellents, pigments, flow additives, UV absorbers and a broad-spectrum fungicide.



Product Code

Morning Grey:	30610942
Teak:	30806029
Mid Oak:	30806032
Light Oak:	30806035
Cream:	30806038
Red Cedar:	30806042
Walnut:	30806044
Black:	30806047
Mahogany:	30806050
Pine:	30806054
White:	30806057
Spruce:	30806060
Antique Pine:	30806063

Description

Sovereign SX70 Woodstain is a high quality solvent based woodstain, containing a flexible alkyd resin along with water repellents, pigments, flow additives, UV absorbers and a broad-spectrum fungicide.

Sovereign SX70 Woodstains are compatible with the SX70 range of Basecoats and Topcoat.

Form Supplied: Liquid, ready to use

Pack Sizes: 5 litres

Colour Range: Teak, Red Cedar, Walnut, Black, Mahogany, Pine, White, Spruce, Antique Pine, Mid Oak, Light Oak, Cream, Morning Grey

Contains: Long oil alkyd resin and speciality additives

Properties

Suitable for all types of soft and hardwood to give a decorative wood finish which is tough, durable, flexible and water resistant in all types of situations, e.g. on doors, windows, skirtings, dado rails, panelling, soffits, barge boards, etc.



PREPARATION/USAGE

Surfaces must be sound, clean and dry before coating. Timber must have a moisture content of less than 18%. Existing paint coating must be fully removed back to clean, bare timber. Previously stained timber should have any loose flaky material removed and then the surfaces lightly sanded in the direction of the grain. Moss, mould and algae should be treated with Sovereign Dentolite, the growths removed and the timber allowed to dry. Clean all surfaces of timber with methylated spirit. Some timbers contain extractives that can bleed through coatings; a trial application is recommended.

Resinous deposits should be scraped off and cleaned with methylated spirits. Do not use knotting solutions, allow knots to "bleed out" through the coating and remove resin with a scraper when necessary. Non-durable external timber should be treated with Sovereign Timber Preservative.

Stir well before use. Do not use straight from the container, decant a small amount into a suitable receptacle, do not put back part used material into the can.

SX70 is designed to be applied to bare timber or existing wood stains. A minimum of two coats must be applied. Apply using a high quality wood stain brush, working in the direction of the grain using the minimum number of brush strokes.

On new work the first coat should be applied to all sides prior to assembly. End grains should be sealed and the backs of beads and rebates coated and special attention should be given to the tops and bottoms of doors and the underside of sills. Metal fixing must be suitable for external use i.e. stainless steel or galvanised. Nails holes should be filled with Sovereign Wood Filler. Apply the second coat as soon as the first has thoroughly dried, around 24 hours in good conditions. Third and subsequent coats can be applied if a deeper colour or greater protection is required. Do not apply in temperatures below 10°C in damp conditions or when rain is imminent.

MAINTENANCE

Timber should be inspected regularly to ensure integrity of coating. When recoating becomes necessary thoroughly clean and dry the surface and apply one or two coats of SX70.

DRYING TIME

Typically touch dry in 3 - 4 hours and hard dry overnight.

CLEAN UP

Brushes can be cleaned in white spirit

LIMITATIONS

Due to the natural variance in timbers it is essential that the user prepare the timber in the correct manner. Some timber can exude either solvent soluble resins or water soluble tannins that may stain any subsequent coating. If in doubt a test should be carried out. This is especially the case when using white coatings.

COVERAGE

Sanded Pine typically 10-12 m² per litre per coat. Figures for sawn softwood timber will be lower. Hardwood coverage rates may be slightly higher.

COLOUR RANGE

MORNING GREY



TEAK




MID OAK



LIGHT OAK



CREAM




RED CEDAR



WALNUT



BLACK



MAHOGANY



PINE




WHITE



SPRUCE



ANTIQUÉ PINE



UNTREATED SAMPLE



Storage: Between 5°C and 30°C.

Shelf Life: 12 months unopened.

HEALTH & SAFETY

- ! Keep out of reach of children.
- ! Keep away from food, R10 Flammable liquid.
- ! Keep out of reach of children. Keep away from food, drink and animal feeding stuff. When using do not eat, drink or smoke. Avoid contact with skin and eyes.



For full Health & Safety
information see Safety Data
Sheet reference number SDS 15.



Important Disclaimer

The information given is in good faith based on experience and usage, however all recommendations are made without warranty or guarantee, since the conditions of use are beyond our control. All goods are sold in accordance with our Conditions of Sale, copies of which are available on request. Customers are advised that product, techniques and codes of practice are under constant review and changes occur without notice. Please ensure you have the latest updated information.



Sovereign
the gold standard in building products

Sovereign Support: 01229 870800 | www.sovchem.co.uk

FIND US HERE

